

LABORATORY TEST REPORT

Report # 83858 3290-8004 Lab Test Number: **Report Date:**

October 27, 2021

ASTM D5848 Weights www.testingservices.us • (706)226-1400

office@testingservices.us

CLIENT:

| Company: | Turf Distributors | |
|-----------------------------|--------------------|--|
| Address: 42505 Rionedo Road | | |
| | Temecula, CA 92590 | |
| Requested By: | Scott Lindow | |

TEST MATERIAL: Date Material Received: September 27, 2021 Material Type: Synthetic Turf Material Condition: Excellent, New Product Name: Eco 94 Gold

100108-0

TESTING METHODS REQUESTED:

| Testing Services Inc. was instructed by the client to test for the following | | | | | |
|---|------------|--------------|---|--|--|
| Standard: | ASTM D5848 | Test Method: | Standard Test Method for Mass per Unit Area of Pile Yarn Floorcoverings | | |
| SAMPLING PLAN: | | | | | |
| Sampling Date: 9/27/2021 | | 9/27/2021 | | | |
| Specimen sampling is performed in the sampling department at TSI. | | | | | |
| The sampling size of specimens is determined by the test method requirements. | | | | | |

In the event a specific sampling size is not called for, a determination will be made based on previous testing experience, and approved for use by an authorized manager

All samples are subjected to the outside environmental conditions of temperature and relative humidly.

uiring pre-determined exposure to specified environmental conditions based on a specific test method, take place in the departments in which they are tested

DEVIATION FROM TEST METHODS:

State reason for any Deviation from, Additions to, or Exclusions From Test Method.

None

TEAT OUR MANDY

| IEST SUMMARY: | | | | |
|---------------|--------------------------|--------------------------|--|--|
| TEST METHOD | TEST DESCRIPTION | TEST RESULT | | |
| ASTM D5848-20 | Total Product Weight | 96.59 oz/yd ² | | |
| ASTM D5848-20 | Pile Yarn Weight | 67.19 oz/yd ² | | |
| ASTM D5848-20 | Primary Backing Weight | 7.92 oz/yd ² | | |
| ASTM D5848-20 | Secondary Backing Weight | 21.48 oz/yd ² | | |

Torcertainty: We undertake all assignments for our clients on a best effort basis. Our findings and judgments are based on the information to us using the latest test methods available. TSI can only ensure the test results for the specific items tested. Unless otherwise noted in the deviations sections of this report, all tests are performed in compliance with stated test method.

Test Report Approval:

TSi Accreditation:

Erle Miles, III, Lab Director Testing Services (TSI) LLC

Our laboratory is accredited by the US Dept. of Commerce, National Institute of Standards and Technology: ISO/IEC 17025:2005. Our code # is: NVLAP 100108-0. TSi is an Organizational Member of ASTM (American Society for Testing and Materials). TSi is a certified independent testing laboratory by the STC (Synthetic Turf Council).